

Abstract of the Disclosure:

A protective layer has the composition 0.5 to 2% of rhenium, 15 to 21% of chromium, 9 to 11.5% of aluminum, 0.05 to 0.7% of yttrium and/or at least one equivalent metal from the group  
5 consisting of scandium and the rare earths, 0 to 1% of ruthenium, remainder cobalt and/or nickel and production-related impurities, and is scarcely subject to any embrittlement from Cr/Re precipitations.